

Parobarrier N90

 Type: A B V

Valid from 01.01.2013

PROPERTIES	METHOD	UNITS	NOMINAL VALUE	TOLERANCE	
				MINIMUM	MAXIMUM

Informative section:


Length	EN 1848-2	[m]	50	-	-
Width	EN 1848-2	[m]	1,5; 3	-0,5%	+1,5%
Straightness	EN 1848-2	-	conforming	-	-
Thickness	EN 1849-2	[mm]	0,17	-0,02	+0,02
Mass per unit area	EN 1849-2	[g/m ²]	90	-10	+10
Visible defects	EN 1850-2	-	without visible defects		

Normative part:

Reaction to fire	EN 13501-1 EN 11925-2	[class]	F	-	-
Water tightness	EN 1928	-	conforming	-	-
Water vapour transmission properties (Sd)	EN 1931	[m]	35	-10	+10
Maximum tensile force MD/CMD	EN 12311-2 EN 13859-1	[N/50mm]	>210 / >190	-	-
Elongation MD/CMD	EN 12311-2 EN 13859-1	[%]	>15 / >15	-	-
Resistance to tearing MD/CMD	EN 12310-2 EN 13859-1	[N]	>135 / >125	-	-
Determination of resistance to impact	EN 12691	-	npd	-	-
Joint strength	EN 12317-2	[N]	npd	-	-
Resistance to deformation under load	EN 13984	-	npd	-	-
Resistance to alkali	EN 13984 EN 12311-2	-	npd	-	-
Durability of water vapour resistance against ageing	EN 1296 EN 1931	-	conforming	-	-

Notes: MD - Machine Direction, CMD - Cross Machine Direction, npd - no performance determined

PRODUCT APPLICATION



EN 13984

Universal reinforced barrier consisting of polyethylene sheet reinforced with a tear-resistant mesh to be used against vapour and moisture penetration in pitched or flat roof construction, vertical wall construction or in ceiling, placed parallel or crosswise onto the rafters, directly beneath the thermal insulation. All overlaps should be sealed with recommended special sealing tapes.

This product does not contain any dangerous substances.